

Product Class: Rubber

| <u>Property</u> | <u>Test Method</u> | <u>Typical Result</u> |
|-------------------------------|--------------------|---|
| Density | ASTM D297 | 53 lbs./ft ³ (0.85 g/cm ³) |
| Tensile Strength | ASTM D412, Die C | 200 lbs./in ² (1.4 MPa) |
| Elongation | ASTM D412, Die C | 95% |
| Tear Strength | ASTM D624, Die C | 70 lbs./in. (12 N/mm) |
| Shore A Hardness | ASTM D2240 | 55 |
| Flexibility | ASTM F147 | 1 |
| Compression @ 100 psi | ASTM F36 | 18% |
| Recovery | | 91% |
| Compression Set B | ASTM D395 | 36% |
| 25% deflection, 22 hrs. 158°F | | |
| Force Reduction | Deltec | 18% for 10mm 7619-II |
| Energy Restitution | Deltec | 67% for 10mm 7619-II |
| Coefficient of Friction | ASTM D4521 | 1.0 |

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

The values shown represent current production and may vary under different conditions.

Document #: CRP01.RD.PSL.PS.0013
 Revision #: 2
 Revision (Date) 8/1/2022
 Expiration Date 8/1/2025
 Approved By: W.Welch

| | | | | |
|-----------|--------------------------------|--|--|--|
| Doc Name: | Public Spec 7619-II &7619NT-II | | | |
|-----------|--------------------------------|--|--|--|

| Revision | Date | Revised | Changes |
|----------|-----------|---------|-----------------------------------|
| New | 6/21/2016 | W.Welch | Creation of the Public Spec. |
| 1 | 6/7/2019 | W.Welch | Three year review; no change. |
| 2 | 8/1/2022 | W.Welch | Added Deltec; updated T, Te, H, C |