

Product Class: Composition Cork

| <u>Property</u> | <u>Test Method</u> | <u>Typical Result</u> |
|------------------------|---------------------------|-----------------------------------------------------|
| Density | ASTM D3676 | 23.9 lbs./ft ³ (0.22 g/cm ³) |
| Tensile Strength | ASTM F152 | 88 lbs./in ² (607 kPa) |
| Compression @ 100 psi | ASTM F36 | 48% |
| Recovery | | 84% |
| Flexibility | ASTM F147 | 5 max. |

This material has a shelf life of 2 years from date of manufacture when protected from environmental extremes.

The values shown represent current production and may vary under different conditions.

PS 133 1462 (8017)
REV 101015
WMW