

**Product Class: Rubber**

<u>Property</u>	<u>Test Method</u>	<u>Typical Result</u>
Density	ASTM D297	56 lbs./ft <sup>3</sup> (0.90 g/cm <sup>3</sup> )
Tensile Strength	ASTM D412, Die C	270 lbs./in <sup>2</sup> (1860 kPa)
Tear Strength	ASTM D624, Die C	90 lbs./in. (16 N/mm)
Shore A Hardness	ASTM D2240	60
Flexibility	ASTM F147	1
Coefficient of Friction	ASTM D4521	1.2

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

*The values shown represent current production and may vary under different conditions.*

Document #: CRP01.RD.PSL.PS.0014

Revision #: 2

Revision (Date): 8/1/2022

Expiration Date: 8/1/2025

Approved By: W.Welch

Doc Name:	Public Spec 7619-III (8050)				
Doc Revision:	New				
Issue Date:	6/21/2016				
Written By:	W.Welch				
Checked By:	N/A				

Revision	Date	Revised by	Changes
New	6/21/2016	W.Welch	Creation of the Public Spec.
1	6/7/2019	W.Welch	Three year review; no change.
2	8/1/2022	W.Welch	Added part number; removed Elongation.