

Product Class: Cork / Rubber

Property	Test Method	Typical R	<u>lesult</u>
Density	ASTM D3676	48.4 lbs./	ft ³ (0.78 g/cm ³)
Tensile Strength	ASTM F152	350 lbs./iı	n² (2.4 MPa)
Compression @ 300 psi		25%	(Recovery 95%)
@ 400 ps	SI	32%	(Recovery 83%)
Flexibility	ASTM F147	3 max.	
Shore A Hardness	ASTM D2240	70	
Compression Set B	ASTM D395	60% max	
25% deflection, 22 h	nrs. @ 158°F		
Fluid Immersion	ASTM F146	change in volume	
Oil 1	70 hrs. @ 212°F	-2 to +20%	
Oil 3	70 hrs. @ 212°F	+5 to +35%	
Fuel A	22 hrs. @ 75°F	0 to +15%	

Temperature Range - 40° to + 250°F (-40° to + 121°C)

Meets the following specs: ASTM F104 F226000 M2 T

MIL-G-12803 P2255A (superseded in 1997 by ASTM F104) AMS-C-6183 (previously MIL-C-6183b) Type I or II, CI 2, Gr B

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

The values shown represent current production and may vary under different conditions.

Document #: CRP01.RD.PSL.PS.0038

Revision #: 2

Revision (Date): 8/1/2022 Expiration Date: 8/1/2025 Approved By: W.Welch Doc Name: Public Spec E40 (8016)

Revision	Date	Revised by	Changes
New	6/21/2016	W.Welch	Creation of the Public Spec.
1	6/7/2019	W.Welch	Three year review; no change.
2	8/1/2022	W.Welch	Removed 100N; added part number;