

Product Class: Cork / Rubber

<u>Property</u>	<u>Test Method</u>	<u>Typical Result</u>
Density	ASTM D3676	45.9 lbs./ft ³ (0.74 g/cm ³)
Tensile Strength	ASTM F152	325 lbs./in ² (2.2 MPa)
Compression @ 300 psi	ASTM F36	27% (Recovery 95%)
@ 400 psi		33% (Recovery 82%)
Flexibility	ASTM F147	3 max.
Shore A Hardness	ASTM D2240	68
Compression Set B	ASTM D395	80% max
25% deflection, 22 hrs. @ 158°F		
Fluid Immersion	ASTM F146	change in volume
Oil 1	70 hrs. @ 212°F	-5 to +10%
Oil 3	70 hrs. @ 212°F	0 to +20%
Fuel A	22 hrs. @ 75°F	0 to +15%
Temperature Range	- 40° to + 250°F (-40° to + 121°C)	
Meets the following specs:	ASTM F104 F226000 M2 T MIL-G-12803 P2255A (superseded in 1997 by ASTM F104) AMS-C-6183 (MIL-C-6183b) Type I or II, Cl 1, Gr B	

This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

The values shown represent current production and may vary under different conditions.

Document #: CRP01.RD.PSL.PS.0044
Revision #: 2
Revision (Date): 8/1/2022
Expiration Date: 8/1/2025
Approved By: W.Welch

Uncontrolled Document When Printed
Printed: 8/23/2022

715 Fountain Avenue,
Lancaster, PA 17601
phone: 717.295.3400

Doc Name:	Public Spec H45 (8031)				
Doc Revision:	New				
Issue Date:	6/21/2016				
Written By:	W. Welch				
Checked By:	N/A				

Revision	Date	Revised by	Changes
New	6/21/2019	W.Welch	Creation of the Public Spec.
1	6/7/2019	W.Welch	Three year review; no change.
2	8/1/2022	W.Welch	Added part number; updated